

Starex VH-0800 E

Acrylonitrile Butadiene Styrene
LOTTE ADVANCED MATERIALS CO., LTD.

Message:

Starex VH-0800 E is an acrylonitrile butadiene styrene (ABS) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The application areas of Starex VH-0800 E include electrical/electronic applications and electrical appliances.

Features include:
flame retardant/rated flame
Flame Retardant

General Information			
UL YellowCard	E115797-219602		
Features	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Electrical appliances		

Physical	Nominal Value	Unit	Test Method
Specific Gravity (Natural)	1.16	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow: 3.20mm	0.24 - 0.29	%	ASTM D955
Transverse flow: 3.20mm	0.26 - 0.32	%	ASTM D955
Lateral flow: 3.20mm	0.26 - 0.32	%	ISO 2577
Traffic: 3.20mm	0.24 - 0.29	%	ISO 2577

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	103		ASTM D785
R scale	108		ISO 2039-2

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2200	MPa	ASTM D638
--	2500	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	39.0	MPa	ASTM D638
Yield	45.0	MPa	ISO 527-2/50
Fracture ³	32.0	MPa	ASTM D638
Fracture	36.0	MPa	ISO 527-2/50
Tensile Elongation			
Fracture ⁴	16	%	ASTM D638
Fracture	8.4	%	ISO 527-2/50
Flexural Modulus			

-- ⁵	2200	MPa	ASTM D790
-- ⁶	2600	MPa	ISO 178
Flexural Strength			
-- ⁷	59.0	MPa	ASTM D790
-- ⁸	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	19	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	200	J/m	ASTM D256
23°C, 6.35 mm	200	J/m	ASTM D256
23°C ¹⁰	18	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, unannealed, 4.00mm	81.0	°C	ISO 75-2/B
0.45 MPa, annealing, 4.00mm	85.0	°C	ISO 75-2/B
1.8 MPa, unannealed, 6.40mm	76.0	°C	ASTM D648
1.8 MPa, not annealed, 4.00mm	71.0	°C	ISO 75-2/A
1.8 MPa, annealing, 4.00mm	80.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	85.0	°C	ISO 306/B50
--	88.0	°C	ISO 306/B120
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.5 mm	V-0		UL 94
3.0 mm	V-0		UL 94
6.0 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			
--	80	°C	
Hot air dryer	80	°C	
Drying Time			
--	2.0 - 4.0	hr	
Hot air dryer	2.0 - 3.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	160 - 180	°C	
Middle Temperature	190 - 200	°C	
Front Temperature	210 - 220	°C	
Nozzle Temperature	220	°C	
Mold Temperature	40 - 80	°C	
Injection Pressure	49.0 - 147	MPa	
Back Pressure	0.490 - 1.96	MPa	
Screw Speed	50 - 150	rpm	

NOTE	
1.	5.0 mm/min
2.	5.0 mm/min
3.	5.0 mm/min
4.	5.0 mm/min
5.	2.8 mm/min
6.	2.0 mm/min
7.	2.8 mm/min
8.	2.0 mm/min
9.	Thickness: 4mm
10.	Thickness: 4mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

