Braskem PP TI6200Q4

Polypropylene Impact Copolymer

Braskem America Inc.

Message:

Sub-group

High Impact Copolymer

Description

Extra high izod impact, superior low temperature drop impact, good paint adhesion

Applications

Suggested uses include toys, compounding

General Information			
Features	Food Contact Acceptable		
	High Impact Resistance		
	Impact Copolymer		
	Low Temperature Impact Resistance		
	Paintable		
Uses	Compounding		
Uses	Compounding		
	Toys		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Compounding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	66		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	19.7	MPa	ASTM D638
Tensile Elongation ² (Yield)	5.5	%	ASTM D638
Flexural Modulus - 1% Secant ³	793	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256A
Instrumented Dart Impact (-29°C)	47.5	J	ASTM D3763
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2