

# Tenite™ Butyrate 572E3720008, Clear, Trsp

Cellulose Acetate Butyrate  
Eastman Chemical Company

## Message:

Tenite™ cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of Tenite™ cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite™ cellulosic plastics are available in natural, clear, selected ambers or smoke transparents and black transluents. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite™ Cellulose Acetate Butyrate 572-08 contains an odor mask lubricant and an ultra-violet inhibitor(UVI). It has a plasticizer level of 8%.

General Information	
Additive	Plasticizer (8%) UV Stabilizer
Features	Good Strength Good Toughness Good UV Resistance High Clarity High Gloss High Hardness Low to No Odor Plasticized Renewable Resource Content Soft
Uses	Profiles
Appearance	Amber Black Clear/Transparent Natural Color
Forms	Pellets

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.  
Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

