Adell PP RR-19

Polypropylene Copolymer

Adell Plastics, Inc.

Message:

Adell PP RR-19 is a Polypropylene Copolymer (PP Copolymer) material filled with 43% glass fiber. It is available in North America. Important attributes of Adell PP RR-19 are:

Flame Rated

Copolymer

Impact Resistant

Typical application of Adell PP RR-19: Automotive

| General Information | | | |
|---------------------------------------|----------------------------------|-------|-------------|
| Filler / Reinforcement | Glass Fiber,43% Filler by Weight | | |
| Features | Copolymer | | |
| | High Impact Resistance | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.04 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 1.0 to 1.4 | % | ASTM D955 |
| Water Absorption (24 hr) | 0.030 | % | ASTM D570 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness | | | ASTM D785 |
| M-Scale | 45 | | |
| R-Scale | 66 | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 63.4 | МРа | ASTM D638 |
| Tensile Elongation (Break) | 6.0 | % | ASTM D638 |
| Flexural Modulus | 6890 | МРа | ASTM D790 |
| Flexural Strength | 105 | МРа | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm) | 160 | J/m | ASTM D256 |
| Unnotched Izod Impact (23°C, 3.18 mm) | 530 | J/m | ASTM D256 |
| Gardner Impact | 1.13 | J | ASTM D3029 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load | | | ASTM D648 |
| 0.45 MPa, Unannealed | 159 | °C | |
| 1.8 MPa, Unannealed | 150 | °C | |
| Melting Temperature | 149 to 171 | °C | ASTM D789 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | НВ | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2