

LGG 1042

General Purpose Polystyrene

LG Polymers India Pvt. Ltd.

Message:

LGG 1042 is a High Heat resistance, Very High Molecular Weight GPPS grade having very less Blue tinge.

Applications:

Extruded & foamed products, Advertising boards, window panels etc.

Substitute for Acrylic sheets. Extrusion applications.

General Information			
Features	Ultra high molecular weight Heat resistance, high		
Uses	Foam Sheet		
Appearance	Light Blue		
Forms	Particles		
Processing Method	Extrusion Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	5.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 - 0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	44.1	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	3530	MPa	ASTM D790
Flexural Strength	88.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	12	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	96.0	°C	ASTM D1525
Heat Deflection Temperature - Unannealed	85	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method

Transmittance	95.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	45 - 60	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

