# Zeoforte® ZSC 2295L

### Acrylonitrile Butadiene Rubber

Zeon Chemicals L.P.

#### Message:

Nano-Composite Hydrogenated Nitrile Rubber - Zeon Super Composite

Main Characteristics & Applications

Zetpol composite, new grades with high dimensional stability and low heat-build-up, excellent tear resistance, abrasion resistance and good elongation at high hardness, excellent dynamic properties, used for timing belts, poly-V-belts and printing rollers.

General Information			
Features	Good Abrasion Resistance Good Dimensional Stability Good Tear Strength High Elongation		
	High Hardness		
Uses	Belts/Belt Repair		
	Rollers		
Physical	Nominal Value	Unit	
Specific Gravity	1.24	g/cm³	

Physical	Nominal value	Unit
Specific Gravity	1.24	g/cm³
Mooney Viscosity (ML 1+4, 100°C)	72 to 89	MU
Bound Acrylonitrile <sup>1</sup>	36.0	wt%
lodine Value <sup>2</sup>	28.0	mg/100 mg
NOTE		
1.	Measured on base polymer.	
2.	Measured on base polymer.	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

