

Formolene® 3355O

Polypropylene Random Copolymer

Formosa Plastics Corporation, U.S.A.

Message:

Formolene® 3355O is a high melt flow random copolymer with fast cycle time and easy mold release. It is designed for injection molding including thin wall applications requiring exceptionally good mold and part release. The use of an advanced clarifier with its aesthetic values, yellowness index and low haze, makes it an excellent choice for 'see-through' house wares and rigid packaging.

Formolene® 3355O meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Products" section on our website (<http://www.fpcusa.com/ourproducts.html>).

General Information			
Additive	Clarifier		
Features	Fast Molding Cycle		
	Good Mold Release		
	High Flow		
Uses	Containers		
	Household Goods		
	Transparent Parts		
	Vials		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	55	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	29.0	MPa	ASTM D638
Tensile Elongation ² (Yield)	14	%	ASTM D638
Flexural Modulus - 1% Secant ³	1030	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	85.0	°C	ASTM D648
Additional Information	Nominal Value	Unit	Test Method
Injection Haze Plaque (1.00 mm)	15	%	FTTC 5606
NOTE			
1.	50 mm/min		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

