Ultracast[™] AL Blue Label

Epoxy; Epoxide

Hapco Inc.

Message:

A series of low cost, high performance filled casting systems.

Low shrink, low viscosity, one to one mix ratio, duplicating casting systems that reproduce the finest detail. These systems are easily machined, polished, and hand carved without excess wear to cutting tools. Modifications and repairs are easy.

Excellent for all types of model applications, tooling applications, fixture applications, molds, general duplications, and general casting. No more waiting overnight. No more warped castings. No need for carbide cutters to machine.

When you need fast, exact detail, and accurate duplication, ULTRACAST is the best choice.

| General Information | | | |
|---------------------------------|--|-------|-------------|
| Features | Low Shrinkage | | |
| | Low Viscosity | | |
| | Machinable | | |
| | | | |
| Uses | Molds/Dies/Tools | | |
| Appearance | Aluminum | | |
| Forms | Liquid | | |
| Processing Method | Casting | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.70 | g/cm³ | ASTM D792 |
| Specific Volume | 0.00222 | cm³/g | |
| Gel Time (25°C) | 17.0 | min | |
| Molding Shrinkage - Flow | 0.10 to 0.15 | % | ASTM D955 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 77 to 83 | | ASTM D2240 |
| Thermoset | Nominal Value | Unit | Test Method |
| Thermoset Components | | | |
| Part A | Mix Ratio by Weight: 100, Mix Ratio by Volume: 100 | | |
| Part B | Mix Ratio by Weight: 100, Mix Ratio by Volume: 100 | | |
| Thermoset Mix Viscosity (25°C) | 4950 to 5050 | сР | ASTM D2393 |
| Demold Time ¹ (21°C) | 240 to 480 | min | |
| NOTE | | | |
| 1. | 0.125 inches thick | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

