DuraSurf™ STS

Ultra High Molecular Weight Polyethylene

Crown Plastics

Message:

DuraSurf[™] STS is a revolutionary product in that it not only possesses a Silicone Treated Surface, but is also available with an adhesive backing for easy installation. The very low coefficient of friction provides a lubricated surface that is virtually maintenance free. DuraSurf[™] STS is an ideal solution for many applications in the package handling industry such as chute linings, slider beds, slides, spirals and numerous other areas where packages can get lodged or damaged. DuraSurf[™] STS also helps reduce jamming and keep packages moving smoothly to their ultimate destination. DuraSurf[™] STS is also static dissipative to prevents static shocks and potential damage to bar coding systems. DuraSurf[™] STS is uniquely available with an adhesive backing to provide easy installation and eliminate the need for mechanical fastening. Die cutting is also available for washers, bushings, wear pads and anti-friction surfaces.

AVAILABLE THICKNESS .031" (.75 mm), .062" (1.57 mm), .093" (2.35 mm), .125" (3.17 mm) AVAILABLE WIDTHS All dimensions between 1/4" (6.35 mm) and 24" (610 mm) UHMW PROPERTIES Excellent abrasion and wear resistance Very high impact strength Meets FDA and USDA guidelines No moisture absorption Self-lubricating - no need for oils or lubricants Excellent noise abatement properties Chemical resistance and corrosion resistant Maintains performance and properties at -30°C Meets ASTM-D-4020-81 Low coefficient of friction

General Information	
Features	ESD Protection
	Good Abrasion Resistance
	Good Chemical Resistance
	Good Corrosion Resistance
	Good Wear Resistance
	High Impact Resistance
	Low Friction
	Moisture Resistant
	Noise Damping
	Self Lubricating
Uses	Bushings
	Liners
	Washer
	Wear Strip
Agency Ratings	ASTM D 4020
	FDA Unspecified Rating
	USDA Unspecified Approval

Forms	Preformed Parts		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	0.930	g/cm³	ASTM D792
Crystallinity			ASTM D3417
762.0 μm	48	%	
1.52 mm	47	%	
3.18 mm	50	%	
Relative Viscosity			ASTM D4020
762.0 μm	230 to 350	cm³/g	
1.52 mm	230 to 350	cm³/g	
3.18 mm	230 to 350	cm³/g	
Static Decay			
762.0 μm	< 10	msec	
1.52 mm	< 10	msec	
3.18 mm	< 10	msec	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D, 0.762 mm	65		
Shore D, 1.52 mm	65		
Shore D, 3.18 mm	65		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ASTM D638
0.762 mm	725	MPa	
1.52 mm	731	MPa	
3.18 mm	672	MPa	
Tensile Strength			ASTM D638
Yield, 0.762 mm	23.0	MPa	
Yield, 1.52 mm	20.0	MPa	
Yield, 3.18 mm	22.0	MPa	
Break, 0.762 mm	53.0	MPa	
Break, 1.52 mm	49.0	MPa	
Break, 3.18 mm	44.0	MPa	
Tensile Elongation			ASTM D638
Break, 0.762 mm	60	%	
Break, 1.52 mm	460	%	
Break, 3.18 mm	470	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic ²	0.14		
vs. Itself - Dynamic ³	0.14		
vs. Itself - Dynamic ⁴	0.13		
vs. Itself - Static ⁵	0.16		

vs. Itself - Static ⁶	0.16		
vs. Itself - Static ⁷	0.16		
vs. Steel - Dynamic ⁸	0.050 to 0.080		
vs. Steel - Dynamic ⁹	0.050 to 0.10		
vs. Steel - Dynamic ¹⁰	0.10 to 0.22		
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ¹¹ (3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature			
12	134	°C	
13	136	°C	
CLTE - Flow			ASTM D696
-100 to -20°C, 3.18 mm	9.2E-4	cm/cm/°C	
20 to 100°C, 3.18 mm	1.5E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			ASTM D257
0.762 mm	1.0E+3	ohms	
1.52 mm	1.0E+3	ohms	
3.18 mm	1.0E+3	ohms	
Volume Resistivity			ASTM D257
0.762 mm	6.0E+7	ohms·cm	
1.52 mm	1.5E+7	ohms•cm	
3.18 mm	> 2.0E+7	ohms·cm	
Dielectric Strength (3.18 mm)	14	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
0.762 mm	2.48		
1.52 mm	2.45		
3.18 mm	2.54		
Dissipation Factor			ASTM D150
0.762 mm, 50 Hz	0.059		
0.762 mm, 10 kHz	0.11		
0.762 mm, 5 MHz	0.10		
1.52 mm, 50 Hz	0.021		
1.52 mm, 10 kHz	0.069		
1.52 mm, 5 MHz	0.23		
3.18 mm, 50 Hz	8.2E-3		
3.18 mm, 10 kHz	2.2E-3		
3.18 mm, 5 MHz	3.4E-3		
NOTE			
1.	0.125 inches		
2.	0.03 inches		
3.	0.125 inches		

4.	0.06 inches
5.	0.03 inches
6.	0.06 inches
7.	0.125 inches
8.	Oil
9.	Water
10.	Dry
11.	5.0 mm Notch Depth
12.	0.125 inches
13.	0.03 inches

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

