

POLYSTONE® Safe-Tec L

Thermoplastic

Röchling Engineering Plastics SE & Co. KG

Message:

Product characteristics

High weather resistance

Anti-slip properties even in wet surface

Typical field of application

Step-on surfaces in the toy and leisure equipment

General Information			
Features	Good Weather Resistance		
Uses	Sporting Goods		
	Toys		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	< 0.050	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	59		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	800	MPa	ISO 527-2
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Tensile Strain (Break)	> 50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	12	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature			
-- 1	-30.0 to 100	°C	
-- 2	< 100	°C	
Melting Temperature	135	°C	ISO 11357-3
CLTE - Flow	1.5E-4 to 2.3E-4	cm/cm/°C	DIN 53752
Specific Heat	1900	J/kg/°C	DIN 52612
Thermal Conductivity	0.40	W/m/K	DIN 52612
Heat Deflection Temperature - Vicat B	67	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+14	ohms · cm	IEC 60093
Electric Strength	45	kV/mm	IEC 60243-1
Dielectric Constant	2.50		IEC 60250
Dissipation Factor (1 MHz)	4.0E-4		IEC 60250

Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	HB		
6.00 mm	HB		
NOTE			
1.	Long Term		
2.	Short Term		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT