

Chemlon® 530 GH

Polyamide 66

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® 530 GH is a Polyamide 66 (Nylon 66) material filled with glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Chemlon® 530 GH: Flame Rated.
Typical application of Chemlon® 530 GH: Automotive

General Information			
Filler / Reinforcement	Glass Fiber		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.25 to 0.45	%	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	128	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	2.5	%	
Break	4.0	%	
Flexural Modulus	5520	MPa	ASTM D790
Flexural Strength	176	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	91	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	229	°C	ASTM D648
Melting Temperature	257	°C	
CLTE - Flow	5.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength (3.00 mm)	15	kV/mm	ASTM D149
Comparative Tracking Index (CTI)	600	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.810 mm)	HB		UL 94
Oxygen Index	23	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Suggested Max Moisture	0.20	%	
Suggested Max Regrind	25	%	

Rear Temperature	252 to 268	°C
Middle Temperature	263 to 274	°C
Front Temperature	268 to 285	°C
Nozzle Temperature	268 to 285	°C
Processing (Melt) Temp	263 to 282	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT