

VENYL UN001 - 6733

Polyamide 66

AD majoris

Message:

VENYL UN001 - 6733 is a polyamide 66 lubricated, high heat resistant and coloured with medium viscosity intended for Injection moulding.

APPLICATIONS

VENYL UN001 - 6733 has been developed especially for very demanding applications in automotive industry and electrical parts.

Products requiring excellent combination between thermal and mechanical properties.

VENYL UN001 - 6733 is available in both black (VENYL UN001 - 8229) and natural (VENYL UN001) but other colours can be provided on request.

General Information				
Additive	Lubricant			
Features	High Heat Resistance			
	Lubricated			
	Medium Viscosity			
	Recyclable Material			
Uses	Automotive Applications			
	Electrical Parts			
Appearance	Black			
	Colors Available			
	Natural Color			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage	1.3 to 2.2	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	2.2 to 2.5	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (L-Scale)	103	87		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3000 to 3500	1400 to 1600	MPa	ISO 527-2
Tensile Stress (Break)	85.0 to 95.0	60.0 to 70.0	MPa	ISO 527-2
Tensile Strain (Break)	15 to 50	200 to 300	%	ISO 527-2
Flexural Modulus	2600 to 2900	1300 to 1500	MPa	ISO 178
Flexural Stress	135 to 150	75.0 to 85.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength	3.7 to 5.5	17 to 23	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179
Notched Izod Impact	51 to 660	180 to 200	J/m	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	105	--	°C	ISO 75-2/A
Melting Temperature (DSC)	256	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+12	ohms	DIN 53482
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	DIN 53482
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-2	--		UL 94
Glow Wire Flammability Index (2.00 mm)	850	--	°C	IEC 60695-2-12
Injection	Dry	Unit		
Rear Temperature	260 to 280		°C	
Middle Temperature	255 to 270		°C	
Front Temperature	250 to 265		°C	
Nozzle Temperature	250 to 270		°C	
Mold Temperature	90.0 to 100		°C	
Injection Pressure	60.0 to 100		MPa	
Injection Rate	Fast			
Holding Pressure	35.0 to 60.0		MPa	
Screw L/D Ratio	15.0:1.0 to 20.0:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT