# Indorama PET 1101 B-PET

### Polyethylene Terephthalate

#### Indorama Ventures Polymers México

#### Message:

Indorama PET 1101 B- PET is a polyethylene terephthalate (PET) material. This product is available in Latin America and is processed by stretch blow molding.

The main characteristics of Indorama PET 1101 B- PET are:

environmental protection/green

**Excellent Processability** 

Copolymer

accessible food

Good dimensional stability

Typical application areas include:

container

packing

bottle

food contact applications

| General Information              |                             |       |                 |  |  |
|----------------------------------|-----------------------------|-------|-----------------|--|--|
| Features                         | Excellent Processability    |       |                 |  |  |
|                                  | Good dimensional stability  |       |                 |  |  |
|                                  | Copolymer                   |       |                 |  |  |
|                                  | Updatable resources         |       |                 |  |  |
|                                  | Recyclable materials        |       |                 |  |  |
|                                  | Definition, high            |       |                 |  |  |
|                                  | Compliance of Food Exposure |       |                 |  |  |
|                                  |                             |       |                 |  |  |
| Uses                             | Beverage Containers         |       |                 |  |  |
|                                  | Packaging                   |       |                 |  |  |
|                                  | Bottle                      |       |                 |  |  |
|                                  | Container                   |       |                 |  |  |
|                                  | Food container              |       |                 |  |  |
|                                  |                             |       |                 |  |  |
| Agency Ratings                   | FDA not rated               |       |                 |  |  |
| Processing Method                | Stretch blow molding        |       |                 |  |  |
| Physical                         | Nominal Value               | Unit  | Test Method     |  |  |
| Density                          | 1.40                        | g/cm³ | Internal method |  |  |
| Apparent Density                 |                             |       | Internal method |  |  |
| 1                                | 0.88                        | g/cm³ | Internal method |  |  |
| <sup>2</sup>                     | 0.90                        | g/cm³ | Internal method |  |  |
| Acetaldehyde                     | 0.50                        | ppm   | Internal method |  |  |
| Color b                          | -3.00                       |       | Internal method |  |  |
| Crystallinity                    | 53                          | %     | Internal method |  |  |
| Intrinsic Viscosity <sup>3</sup> | 0.85                        | dl/g  | Internal method |  |  |

|                     | 80.0   |           |                 |  |
|---------------------|--|-----------|-----------------|--|
|                     |  |           |                 |  |
| Chip Size           | 60.0   | pcs/g     | Internal method |  |
| Fines               |  | %         | Internal method |  |
| Yellow Chips        |  | pcs/125 g | Internal method |  |
| Thermal             | Nominal Value  | Unit      | Test Method     |  |
| Melting Temperature | 240  | °C        | Internal method |  |
| NOTE                |  |           |                 |  |
| 1.                  | For 60 pellets/g   |           |                 |  |
| 2.                  | For 80 pellets/g   |           |                 |  |
| 3.                  | Determined by conversion of solution viscosity to intrinsic viscosity using an empirical correlation developed by Indorama Ventures Polymers México. |           |                 |  |

wt%

Internal method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

0.15

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

Moisture Content

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

