

Hostacom EKC 334N

Polypropylene Copolymer
LyondellBasell Industries

Message:

"Hostacom" EKC 334N is a 20% mineral filled PP copolymer with good stifness toughness balance, low odour and fogging. Used typically for automotive interior, in particular for instrument panels.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Features	Copolymer		
	Good Stiffness		
	Good Toughness		
	Low to No Fogging		
	Low to No Odor		
Uses	Automotive Instrument Panel		
	Automotive Interior Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	2400	MPa	ISO 527-2
Tensile Stress (Yield)	25.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	3.0	%	ISO 527-2/50
Flexural Modulus - Secant	2400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	40	kJ/m²	
23°C	95	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	110	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/A50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

