

RTP ESD A 2700-45A

Thermoplastic Elastomer

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Features	Antistatic property		
Agency Ratings	MIL B-81705C		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.5 - 2.5	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	45		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	0.345	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	No Break		ASTM D256
Unnotched Izod Impact (3.18 mm)	No Break		ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9	ohms	ASTM D257
Volume Resistivity	1.0E+6	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.52 mm)	HB		UL 94
Additional Information			
Volume Resistivity, ASTM D257: 1E3-1E9 ohm-cmSurface Resistivity, ASTM D257: 1E6-1E12 ohms/sq			
Injection	Nominal Value	Unit	
Rear Temperature	177 - 232	°C	
Middle Temperature	177 - 232	°C	
Front Temperature	177 - 232	°C	
Mold Temperature	15.6 - 65.6	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

