# NEFTEKHIM PP 8548V

### Polypropylene Copolymer

Nizhnekamskneftekhim Inc.

#### Message:

Product obtained by copolymerization of propylene and ethylene in presence of complex metalorganic catalysts.

It incorporates increased long-term thermal stability, thermal-oxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, antistatic properties to produce and exploit articles, effective nucleation.

Application: thin-wall injection molding

Technical requirements: TU 2211-136-05766801-2006

| General Information                      |                                   |          |             |
|--|-----------------------------------|----------|-------------|
| Additive                                 | Antistatic                        |          |             |
|  | Nucleating Agent                  |          |             |
|  |                                   |          |             |
| Features                                 | Antistatic                        |          |             |
|  | Block Copolymer                   |          |             |
|  | Good Thermal Stability            |          |             |
|  | Nucleated                         |          |             |
|  | Oxidation Resistant               |          |             |
| Uses                                     | Thin-walled Parts                 |          |             |
| Forms                                    | Pellets                           |          |             |
| Processing Method                        | Injection Molding                 |          |             |
| Physical                                 | Nominal Value                     | Unit     | Test Method |
| Density                                  | 0.900                             | g/cm³    |             |
| Apparent Density                         | 0.48 to 0.60                      | g/cm³    |             |
| Melt Mass-Flow Rate (MFR) (230°C/2.16    |                                   |          |             |
| kg)                                      | 85 to 120                         | g/10 min | ASTM D1238  |
| Ash Content                              | 0.025 to 0.050                    | %        |             |
| Thermal Creep Temperature <sup>1</sup>   | 64 to 90                          | °C       |             |
| Thermal-oxidative Deterioration (150°C)  | 15.0                              | day      |             |
| Hardness                                 | Nominal Value                     | Unit     | Test Method |
| Rockwell Hardness (R-Scale)              | 40 to 88                          |          |             |
| Mechanical                               | Nominal Value                     | Unit     | Test Method |
| Flexural Modulus                         | 1300                              | МРа      | ASTM D790   |
| Impact                                   | Nominal Value                     | Unit     | Test Method |
| Notched Izod Impact (23°C)               | 28                                | J/m      | ASTM D256   |
| Thermal                                  | Nominal Value                     | Unit     |             |
| Vicat Softening Temperature <sup>2</sup> | 126 to 150                        | °C       |             |
| NOTE                                     |                                   |          |             |
| 1.                                       | at load 0.46 H/mm²                |          |             |
| 2.                                       | in liquid medium under force 10 H |          |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

