

Precision Polymer N63B

Acrylonitrile Butadiene Rubber
Precision Polymer Engineering Ltd.

Message:

N63B is a Copolymer of acrylonitrile and butadiene with a medium ACN content of 30 - 45%.
NBR materials typically provide excellent resistance to petroleum-based oils, fuels and greases, as well as, very low gas permeability, ozone resistance, plus exceptional heat ageing and mechanical properties.
N63B is accepted by the UK Ministry of Defence (MOD) to Defence Standard 02-337 part 1, issue 1 (NES 337) for use on naval ships and submarines.
Material code MN60.
Available in any sized O-ring (fully moulded up to 2.5m/8ft internal diameter) and custom designed components.
Key Attributes
Excellent resistance to aliphatic hydrocarbon oils, fuels and greases.
Very low gas permeability
Accepted by M.O.D. to Def. Stan. NES 337
Typical Applications
Naval ships and submarines
Aerospace applications

General Information			
Features	Copolymer		
	Good heat aging resistance		
	Ozone resistance		
	Fuel resistance		
	Oil resistance		
	Grease resistance		
Uses	Ship application		
	Aerospace applications		
Appearance	Black		
Hardness	Nominal Value	Test Method	
IRHD Hardness	62	ASTM D1415, ISO 48	
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	17.2	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	400	%	ASTM D412, ISO 37
Compression Set (70°C, 24 hr)	6.0	%	ASTM D395, ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (100°C, 168 hr)	-5.0	%	ASTM D412, ISO 37
Change in Ultimate Elongation in Air (100°C, 168 hr)	-27	%	ASTM D412, ISO 37
Change in IRHD Hardness in Air (100°C, 168 hr)	3.0		ASTM D573, ISO 188
Thermal	Nominal Value	Unit	
Maximum Operating Temperature	120	°C	

Low Temperature Resistance - Non-brittle
after 3 mins

-25

°C

Additional Information

Nominal Value

Unit

Minimum Operating Temperature: -35°C (-31°F)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

