

Ravaflex EPM P

Ethylene Propylene Copolymer

Ravago Group

Message:

Reprocessed free-flowing copolymer of ethylene and propylene with a very good processibility.

General Information			
Features	Copolymer		
	Antioxidation		
	Workability, good		
Appearance	White		
	White-like		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.865 - 0.875	g/cm ³	ASTM D297
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.75 - 0.95	g/10 min	ISO 1133
Mooney Viscosity (ML 1+4, 121°C)	15 - 35	MU	ASTM D1646
Ethylene Content	65.0 - 75.0	wt%	ASTM D3900
Antioxidant Additive	Nonstaining		
Moisture Content (105°C)		%	Internal method
Ash content-1 hr (550°C)		%	ASTM D297
Packaging	1200	g	
Additional Information	Nominal Value	Unit	

It shows an excellent resistance to oxidative and ozone degradation. It is used in bitumen and in plastics modification.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT