

ESTASAN SAN 0840 GF

Styrene Acrylonitrile

Cossa Polimeri S.r.l.

Message:

ESTASAN SAN 0840 GF is a Styrene Acrylonitrile (SAN) product filled with 20% glass fiber. It is available in Europe. Applications of ESTASAN SAN 0840 GF include appliances, automotive and housings.

Characteristics include:

Flame Rated

Good Dimensional Stability

Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Dimensional Stability		
	High Heat Resistance		
Uses	Appliances		
	Automotive Applications		
	Housings		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	82.0	MPa	ASTM D638
Tensile Elongation (Break)	1.4	%	ASTM D638
Flexural Modulus	7400	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	25	J/m	
23°C	30	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	107	°C	ASTM D1525 ¹
--	103	°C	ASTM D1525 ²
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		

NOTE

- | | |
|----|-----------------------------------|
| 1. | Rate A (50°C/h), Loading 1 (10 N) |
| 2. | Rate A (50°C/h), Loading 2 (50 N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

