

AVP™ TLL12CP

Polycarbonate
SABIC Innovative Plastics

Message:

AVP™ TLL12CP is a Polycarbonate (PC) product. It can be processed by injection molding and is available in North America. Applications of AVP™ TLL12CP include electrical/electronic applications, appliances and automotive.

Characteristics include:

- Eco-Friendly/Green
- Good Toughness
- High Strength
- Rigid

General Information			
UL YellowCard	E121562-100305662		
Recycled Content	Yes		
Features	Good Flow		
	Good Toughness		
	High Rigidity		
	High Strength		
Uses	Appliance Components		
	Automotive Applications		
	Communication Applications		
	Electrical Parts		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 3.18 mm)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2410	MPa	ASTM D638
Tensile Strength (Yield)	58.6	MPa	ASTM D638
Tensile Elongation (Yield)	120	%	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength (Yield)	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	640	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	129	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Drying Time, Maximum	16	hr	
Rear Temperature	266 to 282	°C	
Middle Temperature	271 to 282	°C	
Front Temperature	277 to 293	°C	
Nozzle Temperature	271 to 293	°C	
Processing (Melt) Temp	288 to 316	°C	
Mold Temperature	76.7 to 98.9	°C	
Back Pressure	0.345	MPa	
Screw Speed	40 to 70	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

