

REPOL® B120MA

Polypropylene Impact Copolymer

Reliance Industries Limited

Message:

Repol B120MA is recommended for use in Injection Molding processes where medium impact strength is required. It is an ideal material to use in housewares, thermowares, sanitarywares, furniture, industrial and automotive components. Repol B120MA contains antistatic agent that reduces static charge build-up in products.

General Information			
UL YellowCard	E239367-230526		
Additive	Antistatic		
Features	Food Contact Acceptable		
	General Purpose		
	Medium Impact Resistance		
Uses	Automotive Applications		
	Furniture		
	General Purpose		
	Household Goods		
	Industrial Applications		
Agency Ratings	FDA 21 CFR 177.1520		
	IS 10909		
	IS 10910		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, Injection Molded)	24.0	MPa	ASTM D638
Tensile Elongation ² (Yield, Injection Molded)	10	%	ASTM D638
Flexural Modulus - 1% Secant (Injection Molded)	1100	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Injection Molded)	95.0	°C	ASTM D648
NOTE			

- | | |
|----|-------------------|
| 1. | Type I, 50 mm/min |
| 2. | Type I, 50 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

