

Sinvicomp SIZ4805

Flexible Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

"Sinvicomp" SIZ 4805 is a wire & cable polyvinylchloride compound available in pellet form. SIZ 4805 provides good performance for insulation of electrical wires.

General Information			
Features	Rigidity, high		
Uses	Insulating material		
Agency Ratings	IEC 60227 2		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	41		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	20.0	MPa	IEC 811-1-1
Tensile Elongation (Break)	250	%	IEC 811-1-1
Aging	Nominal Value	Unit	Test Method
Changes in mechanical properties after hot air aging test, 136°C, 240 hr ¹			IEC 811-1-2
Tensile strength change	10	%	IEC 811-1-2
Change in tensile elongation	15	%	IEC 811-1-2
Thermal	Nominal Value	Unit	Test Method
Thermal Stability (200°C)	3.5	hr	BS 2782
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (20°C)	1.0E+14	ohms·cm	BS 2782
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	29	%	ASTM D2863
Additional Information			
Typical temperature profile for processing SINVICOMP compound is from 160°C to 185°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.Feeding zone: 160°CCompression zone: 170°C~180°CMixing zone: 175°C~185°CNozzle/Die Zone: 185°C			
NOTE			
1.	136±2°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT