## ADEKA EH-4351S

Epoxy; Epoxide

Adeka Corporation

Message:

DICY type, rapid curing

One and before ation			
General Information			
Features	Fast curing		
Physical	Nominal Value	Unit	
Particle size-(d50)	5.00	μm	
Composition	5 - 10	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	137	°C	ASTM E1356
Melting Temperature	190	°C	
Uncured Properties	Nominal Value	Unit	
Gel Time (150°C)	2.0	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

