TEKNIFLEX® MED 3014-0200

PP Film

Tekni-Films, a div of Tekni-Plex

Message:

PP based Flexible Film for Medical Fluids

Tekniflex® MED 3014-0200 is an unconventionally extruded flexible polypropylene based flexible film that has excellent clarity compared to conventional tubular PP films. The film shows little or no shrink, up to 140°C (284°F) in MD and TD. The film is suitable for steam sterilisation at 121°C, is puncture and tear resistant, heat sealable and has high moisture barrier properties. This film is plasticizer and halogen free.

General Information			
Features	Good Flexibility		
	Good Tear Strength		
	Halogen Free		
	Heat Sealable		
	High Clarity		
	Low Shrinkage		
	Moisture Barrier		
	Puncture Resistant		
	Steam Sterilizable		
Uses	Medical/Healthcare Applications		
Agency Ratings	EP Monograph 3.1.3		
	EP Monograph 3.1.6		
	EP Monograph 3.2.2		
	USP Class VI		
Appearance	Clear/Transparent		
Forms	Film		
Physical	Nominal Value	Unit	
Specific Gravity	0.890	g/cm³	
Dimensional Stability ¹ (140°C)	1.2	%	
Films	Nominal Value	Unit	
Film Thickness ²	200	μт	
Yield	5.62	m²/kg	
Roll Width ³	< 125.00	cm	
Tensile Elongation			
MD : Break	670	%	
TD : Break	740	%	
Seal Initiation Temperature	140 to 150	°C	
Oxygen Transmission Rate (23°C, 90% RH)	1100	cm³/m²/24 hr	

Water Vapor Transmission Rate (38°C, 909	6	
RH)	2.7	g/m²/24 hr
Optical	Nominal Value	Unit
Haze	< 3.0	%
NOTE		
1.	10 minutes	
2.	Thickness tolerance: ±5%	
3.	Roll width tolerance: ±1.5 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

