# HTM® 552

### Maleic Anhydride Grafted Polymer

#### Cytec Industries Inc.

#### Message:

HTM® 552 is a bismaleimide resin matrix formulation that combines high temperature end-use performance with good handleability during lay-up HTM552 has been developed for use in structures where critical load-bearing performance is required at temperatures greater than 200°C (392°F). In applications where components may be lightly loaded, intermittent periods at 250°C (482°F) can be sustained HTM552 is also capable of enduring very short-term exposure to a temperature of 280°C (536°F).

General Information		
Features	Good Processability	
	High Flow	
	High Heat Resistance	
Uses	Structural Parts	
Forms	Fabric	
Physical	Nominal Value	Unit
Specific Gravity <sup>1</sup>	1.21	g/cm³
NOTE		
1.	Cured resin	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

