

Starflam BFR200Y

Polyamide 6
Eurostar Engineering Plastics

Message:

Starflam BFR200Y is Unfilled, Halogen Free and Red Phosphorous Free Flame Retardant Polyamide 6 Injection Molding Resin

General Information			
UL YellowCard	E340012-100750683		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
	Low (to None) Phosphorus Content		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.80 to 1.2	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	9.0	%	
Equilibrium, 23°C, 50% RH	2.2	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3400	MPa	ISO 527-2/1
Tensile Stress (Yield)	78.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	3.7	%	
Break	5.6	%	
Flexural Modulus ²	3100	MPa	ISO 178
Flexural Stress	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³			ISO 179/1eA
-30°C	3.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Charpy Unnotched Impact Strength ⁴			ISO 179/1eU
-30°C	> 100	kJ/m ²	
23°C	> 100	kJ/m ²	
Notched Izod Impact Strength ⁵			ISO 180/1A
-20°C	4.0	kJ/m ²	

23°C	5.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁶			
0.45 MPa, Unannealed, 100 mm Span	190	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	75.0	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	205	°C	ISO 306/B50
--	200	°C	ISO 306/B120
Ball Pressure Test ⁷ (125°C)	Pass		IEC 60695-10-2
CLTE			ISO 11359-2
Flow : 23 to 60°C	7.5E-5	cm/cm/°C	
Transverse : 23 to 60°C	8.0E-5	cm/cm/°C	
RTI Elec	130	°C	UL 746
RTI Imp	90.0	°C	UL 746
RTI Str	100	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁸	> 1.0E+16	ohms	IEC 60093
Volume Resistivity	> 1.0E+16	ohms·cm	IEC 60093
Electric Strength (3.20 mm, in Oil)	15	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	3.30		
60 Hz	3.30		
1 MHz	3.00		
Dissipation Factor			IEC 60250
50 Hz	7.8E-3		
60 Hz	7.8E-3		
1 MHz	0.019		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Oxygen Index	32	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	240 to 250	°C	
Middle Temperature	250 to 260	°C	
Front Temperature	250 to 270	°C	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	50.0 to 90.0	°C	
NOTE			

1.	Tensile Bar
2.	2.0 mm/min
3.	80*10*4 sp=62mm
4.	80*10*4 sp=62mm
5.	80*10*4
6.	120*10*4
7.	125°C ±2°C
8.	ROA

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

