

# ISOTHANE® 8102-B

Thermoplastic Polyurethane Elastomer

Great Eastern Resins Industrial Co Ltd (GRECO)

## Message:

ISOTHANE 8102-B product is a toughened engineering thermoplastic polyurethane resin. It exhibits excellent bio-compatibility, hydrolytic resistance, fungus resistance, tensile and flexural strength, toughness, solvent resistance, abrasive resistance, good fatigue resistance, and maintenance of good physical properties under UV exposure. The product can be injection molded and extruded.

General Information			
Features	Biocompatible		
	Fatigue Resistant		
	Fungus Resistant		
	Good Abrasion Resistance		
	Good UV Resistance		
	High Strength		
	High Tensile Strength		
	Hydrolysis Resistant		
	Solvent Resistant		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (224°C/5.0 kg)	5.4	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ASTM D638
Tensile Strength (Yield)	52.0	MPa	ASTM D638
Tensile Elongation (Break)	130	%	ASTM D638
Flexural Modulus	1580	MPa	ASTM D790
Flexural Strength	75.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>1</sup> (23°C)	910	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	92.0	°C	ASTM D1525
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Suggested Max Moisture	< 0.020	%	
Rear Temperature	200 to 205	°C	

Middle Temperature	210 to 220	°C
Front Temperature	210 to 220	°C
Nozzle Temperature	220 to 230	°C
Processing (Melt) Temp	220 to 240	°C
Mold Temperature	65.0 to 85.0	°C

NOTE

1. 3.2 mm Notch Depth

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

