

SUSTAPEEK MG black

Polyetheretherketone

Röchling Sustaplast SE & Co. KG

Message:

- Product characteristics
- High purity
- USP VI and ISO 10993 tested on semi-finished products
- Very good sterilisation resistance
- Typical fields of application
- Medical technology
- Pharmaceutical industry
- Precision engineering

General Information			
Features	High Purity		
Uses	Engineered Applications		
	Medical Devices		
	Medical/Healthcare Applications		
	Pharmaceuticals		
Agency Ratings	ISO 10993		
	USP Class VI		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	88		ISO 868
Ball Indentation Hardness	230	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4000	MPa	ISO 527-2
Tensile Stress (Yield)	110	MPa	ISO 527-2
Tensile Strain (Break)	15	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	152	°C	ISO 75-2/A
Continuous Use Temperature			
-- 1	-60.0 to 250	°C	
-- 2	< 310	°C	
Melting Temperature	343	°C	ISO 11357-3
CLTE - Flow	5.0E-5	cm/cm/°C	DIN 53752

Specific Heat	1340	J/kg/°C	DIN 52612
Thermal Conductivity	0.25	W/m/K	DIN 52612
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		
NOTE			
1.	Long Term		
2.	Short Term		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

