# Jam HP-LL18XF5N

# Linear Low Density Polyethylene

## Jam Petrochemical Company

#### Message:

HP-LL18XF5 N is a termopolymer of ethylene, propylene & butene-1 for high strength application especially heavy duty shipping sacks, ice bag, frozen food bags, potato bags and agriculture films which have good sealability and excellent puncture resistance. Goods produced from this grade have outstanding toughness, excellent puncture resistance, good heat sealing behavior and excellent machinability on conversion lines. HP-LLDPE's process is easier than conventional LLDPEs and have low gel. HP-LL18XF5 N is a grade without slip additives.

#### Features

Exellent punctuer resistance.

Exellent machinability on conversion lines.

Applications

T-bags & other bags, Food Packaging for frozen products, Agricultural film, Heat seal film, Food Packaging

General Information				
Additive	Anti-caking agent			
	Antioxidation			
Features	High Toughness			
	Low speed solidification crystal point			
	High strength			
	Perforation resistance			
	Anti-caking property			
	Antioxidation			
	Machinable			
	Heat sealable			
	Terpolymer			
Uses	Films			
	Bags			
	Agricultural application			
	Food packaging			
	Heavy packing bag			
Physical	Nominal Value	Unit	Test Method	
Density	0.918 - 0.922	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	0.50	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
Flow: Yield	11.0	MPa	ASTM D638	
Transverse flow: Yield	10.0	MPa	ASTM D638	
Flow: Fracture	40.0	MPa	ASTM D638	

Transverse flow: Fracture	35.0	MPa	ASTM D638
Tensile Elongation			ASTM D638
Flow: Fracture	600	%	ASTM D638
Transverse flow: Fracture	750	%	ASTM D638
Films	Nominal Value	Unit	Test Method
Dart Drop Impact	130	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	240	g	ASTM D1922
TD	400	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	127	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	25		ASTM D2457
Haze	30	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

