

ColorRx® TPV-70A0RX

Thermoplastic Vulcanizate Alloy

LTL Color Compounders, Inc.

Message:

A biocompatible, TPV alloy for healthcare applications. Suitable for a wide range of disposable medical items and for overmolding for soft-touch grips. Excellent flow.

General Information	
Features	Biocompatible
	Good Flow
Uses	Flexible Grips
	Medical/Healthcare Applications
	Overmolding
Agency Ratings	ISO 10993
	USP Class VI

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	70		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	5.31	MPa	ASTM D412
Tensile Elongation (Break)	580	%	ASTM D412
Tear Strength	31.2	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 22 hr	22	%	
70°C, 22 hr	41	%	
100°C, 22 hr	52	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT