

Envir® PA6G30L-BK0704

Polyamide 6

Barnet

Message:

Envir® PA6G30L-BK0704 is a 30% Glass fiber reinforced Nylon 6 molding resin. 6G30L is an excellent utility grade compound that is optimized for properties, process and economics. It is provided Black in color.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Melt Volume-Flow Rate (MVR) (235°C/2.16 kg)	5.00	cm ³ /10min	ASTM D1238
Ash Content	30	%	ASTM D5630
Moisture Content	< 0.20	%	ASTM D6980
Granularity	3.50	g/100 pellets	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9860	MPa	ISO 527-2
Tensile Stress (Break)	140	MPa	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Flexural Modulus	8990	MPa	ISO 178
Flexural Stress	210	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	7.3	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	45	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	220	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT