

# SHIN-A SEB-350FR75

Epoxy; Epoxide

SHIN-A T&C;

Message:

Isocyanate Modified Epoxy (Bromine)

Solvent: Acetone/PM

Features: High Tg CCL

General Information		
Uses	Coating Applications	
	Paint	
	Printed Circuit Boards	
Physical	Nominal Value	Unit
Viscosity (25°C)	< 2.00	Pa·s
Bromine Content	16.5 to 18.0	wt%
Epoxy Equivalent	320 to 380	g/eq
N.V.	74.0 to 76.0	wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT