## SQUARE® LIM3919-60A/B

Silicone Rubber, LSR

Shenzhen SQUARE Silicone Co., Ltd.

## Message:

Liquid silicone rubber material for kitchenwares

**Product Description** 

SQUARE® LIM3919-XXA/B is high strength 2-part liquid silicone rubber suitable for injection molding processes, catalyzed by platinum.

**Key Features** 

Good rebound property

Excellent thermal and cold stability(-60°C to 250°C)

Low yellowing

Outstanding resistance to ageing

Meeting US FDA CFR21. Part .177.2600,EN14350.2

At the temperature of 20°C and in the condition of air-proof, the shelf life is 5 days after mixing A and B, the shelf life will decrease with the increasing of the temperature.

**Applications** 

SQUARE® LIM3919-XXA/B is suitable for making kitchenwares.

General Information			
Features	High strength		
	Thermal stability, good		
Uses	Whale on the sail -		
Uses	Kitchen utensils		
Agency Ratings	FDA 21 CFR 177.2600		
Appearance	Translucent		
Processing Method	Liquid Injection Molding (LIM)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm³	ASTM D792
Molding Shrinkage - Flow	2.0	%	JIS K6301
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	6.50	МРа	ASTM D412
Tensile Elongation (Break)	380	%	ASTM D412
Tear Strength <sup>1</sup>	25.0	kN/m	ASTM D624
Compression Set (175°C, 22 hr)	12	%	DIN 53517
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Component a	Mixing ratio by weight: 1.0		
Component B	Mixing ratio by weight: 1.0		
Pot Life (20°C)	7200	min	
Shelf Life	52	wk	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity	500	Pa·s	DIN 53019

NOTE

1. B mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

