## Karina GRAY PVC COMPOUND 881-18/501-E-IS-BZ

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

## Message:

HEAVY METAL FREE PVC COMPOUND RECOMENDED FOR PROFILES EXTRUSION. ALSO RECOMMENDED FOR PLUGS INJECTION.

General Information			
Uses	Profiles		
	Reflectors		
Appearance	Grey		
Processing Method	Injection Molding		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity <sup>1</sup>	1.41 to 1.47	g/cm³	ASTM D792
Color	ОК		ME 12
Color a	-1.98 to 1.02		ME 12
Color b	-0.740 to 2.26		ME 12
Color L	75.1 to 78.1		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	86 to 90		ASTM D2240

NOTE 24 hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Nominal Value

> 12.6

> 150

Unit

MPa

%

Test Method

ASTM D638

ASTM D638

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Mechanical

Tensile Strength

Tensile Elongation (Yield)

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

