

POLYCHIM B 10 TB

Polypropylene Homopolymer
POLYCHIM INDUSTRIES

Message:

POLYCHIM B 10 TB is a Polypropylene Homopolymer (PP Homopolymer) product. It can be processed by fiber (spinning) extrusion and is available in Europe. Applications of POLYCHIM B 10 TB include fabrics/fibers and packaging. Primary characteristic: homopolymer.

General Information			
Features	Homopolymer		
	Wide Molecular Weight Distribution		
Uses	Fibers		
	Rigid Packaging		
Processing Method	Fiber (Spinning) Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.904	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10 to 14	g/10 min	ASTM D1238
Ash Content	320	mg/kg	ASTM D229
Color - Yi	< 0.0		DIN 6167
Xylene Solubles - Atacticity	< 5.0	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	111		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	35.0	MPa	ASTM D638
Tensile Elongation ² (Yield)	14	%	ASTM D638
Flexural Modulus - 1% Secant ³	< 1650	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	34	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	82.0	°C	
1.8 MPa, Unannealed	54.0	°C	
Vicat Softening Temperature			
--	154	°C	ASTM D1525 ⁴
--	95.0	°C	ASTM D1525 ⁵
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

4.	Loading 1 (10 N)
5.	Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

