

# Petrotene® PP A3 B35 BRCA009 PH335

Polypropylene

Petropol Industry and Trade of Polymers LTDA

Message:

Polypropylene with 35% mineral filler for injection molding with high density and good set of mechanical properties.

General Information			
Filler / Reinforcement	Mineral,35% Filler by Weight		
Features	High Density		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.16 to 2.20	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	3.0 to 15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.90 to 1.1	%	ASTM D955
Water Absorption (Equilibrium)	0.050	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	30.0	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Flexural Strength	45.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	30	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	65.0	°C	ASTM D648
Continuous Use Temperature	90.0	°C	
Vicat Softening Temperature	150	°C	ASTM D1525 <sup>1</sup>
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	40	kV/mm	ASTM D149
Dissipation Factor (1 kHz)	2.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	60.0 to 80.0	°C	
NOTE			
1.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

