Propafilm™ RC160

Polypropylene Alloy Innovia Films Ltd.

Message:

Acrylic Coated Film

Biaxially oriented polypropylene (BOPP) film coated on both sides with an aqueous acrylic (chlorine free) dispersion. RC140/160 are suitable for VFF bag applications in the confectionery industry where good hot-tack properties are required.

General Information				
Features	Antiblocking			
	Flavor & Aroma Barrier			
	Food Contact Acceptable			
	Good Impact Resistance			
	Heat Sealable			
	Hot Tack Strength			
	Low Temperature Heat Sealability			
	Low Temperature Impact Resistance			
	Moisture Barrier			
	Opticals			
	Puncture Resistant			
Uses	Bags			
	Bi-axially Oriented Film			
	Food Service Applications			
	Laminates			
	Packaging			
Forms	Film			
Physical	Nominal Value	Unit	Test Method	
Molding Shrinkage			Internal Method	
Flow: 121°C, 1 min	2.0	%		
Flow: 129°C, 1 min	7.0	%		
Across Flow: 129°C, 1 min	1.0	%		
Mechanical	Nominal Value	Unit	Test Method	
Coefficient of Friction			ASTM D1894	
vs. Itself - Dynamic	0.25			
vs. Itself - Static	0.25			
Films	Nominal Value	Unit	Test Method	
Seal Strength ¹	0.15	N/mm	Internal Method	
	85.0 to 146	°C	Internal Method	
Seal Initiation Temperature ²	03.0 to 110			

Water Vapor Transmission Rate (38°C, 90%			
RH)	4.0	g/m²/24 hr	ASTM F1770
Film Gauge	160		Internal Method
Yield	27.5	m²/kg	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	95		ASTM D2457
Haze ³	1.5	%	ASTM D1003
NOTE			
1.	265°F; 2secs; 15psi		
2.	2secs; 15psi		
3.	Wide angle; 2.5°		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

