

HiFill® ABS GF30 BK

Acrylonitrile Butadiene Styrene

Techmer Engineered Solutions

Message:

HiFill® ABS GF30 BK is an Acrylonitrile Butadiene Styrene (ABS) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	100	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	128	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	400	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	112	°C	
1.8 MPa, Unannealed	103	°C	
CLTE - Flow	2.9E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength ¹	18	kV/mm	ASTM D149
Additional Information	Nominal Value		
TPCI #	1018121		
Injection	Nominal Value	Unit	
Drying Temperature	76.7 to 87.8	°C	
Drying Time	2.0 to 16	hr	
Rear Temperature	216 to 232	°C	

Middle Temperature	221 to 238	°C
Front Temperature	210 to 221	°C
Nozzle Temperature	199 to 221	°C
Processing (Melt) Temp	232 to 260	°C
Mold Temperature	71.1 to 87.8	°C

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT