Nipol® LX851F2

Latex

Zeon Corporation

Message:

Acrylate latex Characteristics Medium-hard. Excellent resistance to discoloration from light and age. Extremely low formaldehyde. Applications Resin cotton, filters and cotton wool. Canvases (impregnated).

| General Information | | | |
|------------------------------|-----------------|-------|-------------|
| Features | Copolymer | | |
| | Crosslinkable | | |
| | Medium Hardness | | |
| | | | |
| Uses | Filters | | |
| Physical | Nominal Value | Unit | |
| Solution Viscosity | 60 | mPa·s | |
| рН | 7.0 | | |
| Surface Tension | 30 | mN/m | |
| Total Solids | 45 | % | |
| Thermal | Nominal Value | Unit | Test Method |
| Glass Transition Temperature | 15.0 | °C | DSC |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

