

# OPTICITE™ SQZ White

Label Film

The Dow Chemical Company

Message:

OPTICITE™ SQZ White Polyolefin Label Film is a white label film for pressure-sensitive applications that require squeezability. Available in 3.5 mil thickness.

General Information			
Appearance	White		
Forms	Film		
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	89	μm	ASTM D374
Film Thickness - Recommended / Available	3.5 mil (87.5 μ)		
Secant Modulus			ASTM D882
1% Secant, MD : 89 μm	621	MPa	
1% Secant, TD : 89 μm	345	MPa	
Tensile Strength			ASTM D882
MD : Break, 89 μm	23.4	MPa	
TD : Break, 89 μm	12.4	MPa	
Tensile Elongation			ASTM D882
MD : Break, 89 μm	230	%	
TD : Break, 89 μm	60	%	
Treatment <sup>1</sup>	55	dyne/cm	ASTM D2578
Yield (88.9 μm)	11.5	m <sup>2</sup> /kg	ASTM D4321
Optical	Nominal Value	Unit	Test Method
Gloss			ASTM D2457
60°, 88.9 μm <sup>2</sup>	20		
60°, 88.9 μm <sup>3</sup>	45		
Opacity	85	%	ASTM D589
NOTE			
1.	Treatment on outside surface only.		
2.	TD		
3.	MD		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

