Thermoset Plastics 350

Epoxy; Epoxide

Thermoset, Lord Chemical Products

Message:

Thermoset Plastics 350 is an Epoxy; Epoxide (Epoxy) material. It is available in North America for casting or encapsulating. Important attributes of Thermoset Plastics 350 are:

Good Flexibility

Heat Resistant

Insulating

Typical application of Thermoset Plastics 350: Wire & Cable

| General Information | | | |
|--------------------------------|-------------------------------|---------|-------------|
| Features | Electrically Insulating | | |
| | Good Flexibility | | |
| | Good Thermal Shock Resistance | | |
| | | | |
| Uses | Electronic Insulation | | |
| Appearance | Clear/Transparent | | |
| Forms | Pellets | | |
| Processing Method | Casting | | |
| | Encapsulating | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.07 | g/cm³ | ASTM D792 |
| Water Absorption (24 hr) | 0.48 | % | ASTM D570 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 65 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 13.8 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 85 | % | ASTM D638 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 130 | J/m | ASTM D256 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | 8.0E+15 | ohms·cm | ASTM D257 |
| Dielectric Constant (1 MHz) | 3.90 | | ASTM D150 |
| Dissipation Factor (1 MHz) | 0.019 | | ASTM D150 |
| Thermoset | Nominal Value | Unit | Test Method |
| Thermoset Components | | | |
| Hardener | Mix Ratio by Weight: 3.0 | | |
| Resin | Mix Ratio by Weight: 2.0 | | |
| Thermoset Mix Viscosity (25°C) | 4000 | сР | ASTM D2393 |
| Demold Time (121°C) | 120 | min | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

