

TECHNYL® A 218 V50 BLACK 21 N

Polyamide 66
Solvay Engineering Plastics

Message:

TECHNYL® A 218 V50 is a polyamide 66, reinforced with 50% of glass fibre, heat stabilized, for injection moulding. This product is available in natural and black colors.

General Information				
UL YellowCard		E44716-235572		
Filler / Reinforcement		Glass Fiber,50% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Appearance		Black		
		Natural Color		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA66-GF50<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.57	--	g/cm³	ISO 1183/A
Molding Shrinkage				Internal Method
Across Flow	0.80	--	%	
Flow	0.44	--	%	
Water Absorption (23°C, 24 hr)	0.60	--	%	ISO 62
Molding Shrinkage Isotropy	0.550	--		Internal Method
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	16200	12500	MPa	ISO 527-2/1A
Tensile Strength				
Break	220	--	MPa	ASTM D638
Break	240	175	MPa	ISO 527-2/1A
Tensile Elongation				
Break	2.0	--	%	ASTM D638
Break	2.0	2.5	%	ISO 527-2/1A
Flexural Modulus				
--	13800	--	MPa	ASTM D790
--	13500	10000	MPa	ISO 178
Flexural Strength	350	--	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	16	18	kJ/m²	ISO 179/1eA

Charpy Unnotched Impact Strength (23°C)	95	97	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
23°C	180	--	J/m	ASTM D256
--	15	17	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	255	--	°C	ASTM D648, ISO 75-2/Af
Melting Temperature	263	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	1.5E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	6.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	35	30	kV/mm	IEC 60243-1
Relative Permittivity	3.70	4.00		IEC 60250
Dissipation Factor	0.010	0.11		IEC 60250
Comparative Tracking Index (Solution A)	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm	HB	--		
1.60 mm	HB	--		
3.20 mm	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.800 mm	650	--	°C	
1.60 mm	650	--	°C	
3.20 mm	700	--	°C	
Oxygen Index	23	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	265 to 275		°C	
Middle Temperature	270 to 280		°C	
Front Temperature	280 to 290		°C	
Mold Temperature	80.0 to 110		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

