# NuSil R7-3521-11

#### Silicone

### **NuSil Technology**

### Message:

The Aircraft Industry has used silicone adhesives and coatings for over five decades. Silicone's ability to maintain its elasticity and low modulus over a broad temperature range provides excellent utility in extreme environments. Recent advances in material technology provide more opportunities for the Aircraft engineer in choosing the best material for an intended application. Examples of NuSil's capabilities in custom silicones for Aircraft are demonstrated in the following sections.

**Electrically Conductive** 

Fuel Resistant

**Fuel Resistance** 

Static Dissipation and Electrically Conductive Silicones

**Ice-Phobic Coatings** 

General Information

Features

General Purpose: Adhesives and Sealants

Comment: Solvent Resistance

|                             | Solvent Resistant                  |       |
|-----------------------------|------------------------------------|-------|
|                             |                                    |       |
| Uses                        | Adhesives                          |       |
|                             | Aircraft Applications              |       |
|                             | Electrical/Electronic Applications |       |
|                             | Sealants                           |       |
|                             |                                    |       |
| Thermoset                   | Nominal Value                      | Unit  |
| Thermoset Components        |                                    |       |
| Part A                      | Mix Ratio by Weight: 1.0           |       |
| Part B                      | Mix Ratio by Weight: 1.0           |       |
| Additional Information      | Nominal Value                      | Unit  |
| Cure System                 | Platinum                           |       |
| Operating Temperature       | -50 to 200                         | °C    |
| Uncured Properties          | Nominal Value                      | Unit  |
| Color                       | Grey                               |       |
| Density                     | 1.27                               | g/cm³ |
| Curing Time (23°C)          | 48                                 | hr    |
| Pot Life                    | 60                                 | min   |
| Cured Properties            | Nominal Value                      | Unit  |
| Shore Hardness (Shore A)    | 30                                 |       |
| Tensile Strength            | 3.45                               | MPa   |
| Tensile Elongation at Break | 260                                | %     |
| Tear Strength               | 6.13                               | kN/m  |
|                             |                                    |       |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2