# LTP CE-2222

### Polyphenylene Sulfide

Chengdu Letian Plastics Co., Ltd

#### Message:

Resin of LTP CE-2200 serials is a kind of engineering plastic with high performance based on PPS. For its excellent electric conduction property, it is mainly applied in thermostatic parts or shell for electric heating instrument. Thermal conduction and insulation materials made by Resin of LTP CE-2200 serials have these characteristic: high temperature control precise, resistance to water, oil-proof, good safety, light weight and wear well.

| General Information                      |   |           |             |  |                    |  |  |
|--|---|-----------|-------------|--|--------------------|--|--|
| Features                                 | Electrically Conductive  Good Wear Resistance  High Heat Resistance |           |             |  |                    |  |  |
|  |   |           |             |  | Moisture Resistant |  |  |
|  |   |           |             |  | Oil Resistant      |  |  |
|  |   |           |             |  |                    |  |  |
| Appearance                               | Colors Available  |           |             |  |                    |  |  |
| Physical                                 | Nominal Value   | Unit      | Test Method |  |                    |  |  |
| Specific Gravity                         | 1.60 to 1.90  | g/cm³     | ASTM D792   |  |                    |  |  |
| Molding Shrinkage <sup>1</sup> (3.00 mm) | 0.50 to 0.80  | %         |             |  |                    |  |  |
| Mechanical                               | Nominal Value   | Unit      | Test Method |  |                    |  |  |
| Tensile Stress                           | 100 to 125  | МРа       | GB/T 1040   |  |                    |  |  |
| Tensile Strain (Break)                   | 1.0   | %         | GB/T 1040   |  |                    |  |  |
| Flexural Modulus                         | 80000   | МРа       | GB/T 1042   |  |                    |  |  |
| Flexural Stress                          | 120 to 150  | МРа       | GB/T 1042   |  |                    |  |  |
| Impact                                   | Nominal Value   | Unit      | Test Method |  |                    |  |  |
| Charpy Notched Impact Strength           | 12  | kJ/m²     | GB/T 1043   |  |                    |  |  |
| Thermal                                  | Nominal Value   | Unit      | Test Method |  |                    |  |  |
| Heat Deflection Temperature              | > 260   | °C        | GB/T 1634   |  |                    |  |  |
| Electrical                               | Nominal Value   | Unit      | Test Method |  |                    |  |  |
| Volume Resistivity                       | 1.0 to 1.0E+2   | ohms · cm | GB/T 1410   |  |                    |  |  |
| NOTE                                     |   |           |             |  |                    |  |  |
| 1.                                       | 80x80x3 mm  |           |             |  |                    |  |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

