Prime Polypro™ J709QG

Polypropylene Copolymer

Prime Polymer Co., Ltd.

Message:

Prime Polypro[™] J709QG is a Polypropylene Copolymer (PP Copolymer) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of Prime Polypro[™] J709QG include engineering/industrial parts and industrial applications. Characteristics include: Antistatic Copolymer Good Weather Resistance Impact Resistant

| General Information | | | |
|--|--|----------|-------------|
| Additive | Antistatic | | |
| Features | Antistatic | | |
| | Block Copolymer | | |
| | Good Weather Resistance | | |
| | High Impact Resistance | | |
| | | | |
| Uses | Industrial Applications | | |
| | Thin-walled Parts | | |
| | | | |
| Agency Ratings | JHOSPA Unspecified Rating [A]PZar-2967-L | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.910 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 55 | g/10 min | ISO 1133 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness | 90 | | ISO 2039-2 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 1200 | MPa | ISO 527-2 |
| Tensile Stress (Yield) | 25.0 | МРа | ISO 527-2 |
| Tensile Strain (Break) | 30 | % | ISO 527-2 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Unnotched Impact Strength | | | ISO 179 |
| -20°C | 2.5 | kJ/m² | |
| 23°C | 5.5 | kJ/m² | |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature (0.45 MPa, | | | |
| Unannealed) | 90.0 | °C | ISO 75-2/B |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

