

LUBEMIX 85 BLACK

Polycarbonate + ABS

LUBEN PLAST srl

Message:

Compound based on blend PC/ABS second choice. Black coloured.

General Information			
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.13 to 1.17	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	15 to 20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000 to 2500	MPa	ISO 527-2/1A/1
Tensile Stress			ISO 527-2/1A/50
Yield	50.0 to 55.0	MPa	
Break	45.0 to 50.0	MPa	
Tensile Strain			ISO 527-2/1A/50
Yield	6.0 to 8.0	%	
Break	45 to 50	%	
Flexural Modulus ¹	1800 to 2300	MPa	ISO 178
Flexural Stress ²	55.0 to 60.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	40 to 45	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Notched Izod Impact			
23°C, 3.20 mm	450 to 500	J/m	ASTM D256A
23°C ³	No Break		ASTM D256
23°C	40 to 45	kJ/m ²	ISO 180/A
23°C ⁴	45 to 50	kJ/m ²	ASTM D256
Unnotched Izod Impact Strength (23°C)	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	115 to 125	°C	ASTM D648
0.45 MPa, Unannealed	120 to 130	°C	ISO 75-2/B
1.8 MPa, Unannealed, 3.20 mm	100 to 110	°C	ASTM D648
Vicat Softening Temperature			
--	125 to 135	°C	ISO 306/A120
--	120 to 130	°C	ISO 306/B120
NOTE			
1.	2.0 mm/min		

2.	2.0 mm/min
3.	Notch E
4.	Notch A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

