

Cri-Line GP-615-65-LV

Fluoroelastomer

Cri-Tech, Inc.

Message:

66% Fluorine copolymers formulated for injection molding. GP-LV compounds also exhibit the improved hot tear resistance of their higher viscosity counterparts.

| General Information | | |
|---------------------------------------------|-------------------|-------------------|
| Features | Copolymer | |
| | General Purpose | |
| | Low Viscosity | |
| Uses | General Purpose | |
| Processing Method | Injection Molding | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 1.82 | g/cm ³ |
| Fluorine Content | 66 | % |
| Hardness | Nominal Value | Unit |
| Durometer Hardness (Shore A) | 61 | |
| Elastomers | Nominal Value | Unit |
| Tensile Stress (100% Strain) | 2.76 | MPa |
| Tensile Strength | 10.8 | MPa |
| Tensile Elongation (Break) | 290 | % |
| Compression Set ¹ (200°C, 22 hr) | 16 | % |
| NOTE | | |
| 1. | Plied discs | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT