

Shinko-Lac® ASA TW25

Acrylonitrile Styrene Acrylate

Mitsubishi Rayon America Inc.

Message:

Shinko-Lac® ASA TW25 is an Acrylonitrile Styrene Acrylate (ASA) material. It is available in North America for injection molding. Primary attribute of Shinko-Lac® ASA TW25: Heat Resistant.

General Information			
Features	High Heat Resistance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	3.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.55	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	47.1	MPa	ASTM D638
Flexural Modulus (23°C)	2260	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	71.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm, Injection Molded	116	°C	
1.8 MPa, Unannealed, 6.35 mm, Injection Molded	103	°C	
Vicat Softening Temperature	117	°C	ISO 306/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT