

# ELASTOSIL® R plus 4110/60

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, HTV

Extrudates, Technical, Plastics and Rubber Processing

Extrudates, food contact, Plastics and Rubber Processing

Extruded parts; tap water and wastewater contact, Plastics and Rubber Processing

General Information			
Features	Fast Cure		
	Food Contact Acceptable		
	General Purpose		
Uses	Industrial Applications		
	Profiles		
	Valves/Valve Parts		
Processing Method	Extrusion		
	Profile Extrusion		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.15	g/cm <sup>3</sup>	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	60		DIN 53505
Tensile Strength	10.5	MPa	DIN 53504
Tensile Elongation at Break	790	%	DIN 53504
Compression Set	11	%	DIN ISO 815-B
Tear Strength	40.0	kN/m	ASTM D624B
Rebound Resilience	55	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT