

Polipom C100

Acetal (POM) Copolymer

Poliblend S.p.a.

Message:

Polipom C100 is an Acetal (POM) Copolymer material. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America.

General Information			
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage	1.8 to 2.2	%	
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ISO 527-2
Tensile Stress (Yield)	55.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	11	%	
Break	70	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	60	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	165	°C	ISO 75-2/B
1.8 MPa, Unannealed	106	°C	ISO 75-2/A
Continuous Use Temperature ¹	80.0	°C	
Vicat Softening Temperature	165	°C	ISO 306/A120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Melting Temperature	175	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	> 600	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	> 3.0	hr	
Processing (Melt) Temp	180 to 200	°C	
Mold Temperature	70.0 to 90.0	°C	
NOTE			
1.	Without Load		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

